

POLYAMIDE RESIN COMPOSITION AND SYNTHETIC RESIN PRODUCT PREPARED THEREFROM

BACKGROUND OF THE INVENTION

Field of the Invention

5 The present invention concerns a polyamide resin composition having excellent gasoline resistance and impact resistance under cold environment, which is applicable to a fuel tube system for a motor vehicle.

Description of the Prior Art

10 In general, polyamide resins are a general term applied to polymers consisting of amide (-CONH-) groups joined by linear aliphatic sections. Representative of the resins are nylon-6,6 obtained by condensation of adipic acid and hexamethylenediamine, and nylon 6, which is a polymerization product of ϵ -caprolactam. An original polyamide introduced to the market as a synthetic fiber is known as 6,6polyamide under the trademark name nylon. However, in these
15 days, the general term 'nylon', instead of polyamide, is widely used.

 Polyamides are very excellent in mechanical strength, abrasion resistance, heat resistance, chemical resistance, electrical insulation and arc resistance, and are thus variously employed to internal or external decorative materials of motors, electrical or electronic components, sporting goods and industrial materials.
20 Since the polyamides suffer from the drawbacks of low compatibility, flexibility, viscosity and workability with rubber, despite numerous applications in internal or external decorative materials for motor vehicles, they have limitations for use in internal tubes of motors or hoses.

 Thus, with a view to overcome the drawbacks of conventional polyamide
25 resins, there is provided a polyamide resin reinforced with a nylon elastomer having

excellent moldability and flexibility. In this regard, U.S. Pat. Nos. 4,230,838, 4,331,786, 4,332,920 and 4,207,410 disclose a polyamide elastomer of polyoxytetramethylene glycol, included in polyether structure, by substituting an elastomer for a chain-limiter having 4 to 19 carbon atoms between amide groups
5 in polyamide.

In addition, U.S. Pat. No. 5,919,865 refers to a high-impact polyamide composition prepared by adding ethylene propylene rubber (EPR), ethylene propylene diene monomer (EPDM) rubber and maleic anhydride modified SEBS-g-MA to the polyamide. U.S. Pat. No. 5,559,185 discloses a thermoplastic resin
10 composition and U.S. Pat. No. 5,688,866 refers to an impact modification of thermoplastics.

However, the polyamide elastomer of polyoxytetramethylene glycol has an average molecular weight of at most 600 to 800. In addition, the elastomers prepared by the above conventional methods do not have excellent flexibility and
15 toughness.

The above compositions are improved in flexibility and impact resistance, but are disadvantageous in that, when they are actually employed as tube materials of a motor fuel system, external appearance and workability become poor and thickness of final articles is irregular. Also, disperability of rubber is lowered and
20 uniform polyamide resin composition is difficult to obtain during extrusion.

With a view to resolve the above problems, a relatively inexpensive rubber and plasticizer capable of providing high gasoline resistance, impact resistance under cold environment, elongation under tension, good external appearance of molded articles and excellent flexibility, and a thickener useful for improvement of
25 workability, are used to yield materials having more excellent flexibility, elongation and impact strength, external appearance and gasoline resistance, compared to conventional nylon elastomer reinforced polyamide resins.

SUMMARY OF THE INVENTION

Aiming to solve the above problems, we, the inventors of the present invention, have developed a novel polyamide resin composition. It is found that, when a rubber having good dispersability, a nylon thickener for obtaining uniformly thick components and uniform workability, a plasticizer of nylon responsible for providing flexibility suitable for motor fuel tube systems, and a core-shell rubber for increasing external appearance, elongation and impact strength, are used, there is yielded a polyamide resin composition which has flexibility, workability, impact resistance under cold environment and external appearance equal to or better than those of conventional nylon elastomer reinforced polyamide resin composition.

Thus, it is an object of the present invention to provide a polyamide resin composition.

It is another object of the present invention to provide a synthetic resin product prepared from the polyamide resin composition.

DETAILED DESCRIPTION OF THE INVENTION

To achieve the objects, the present invention provides a polyamide resin composition comprising (a) 30-95 parts by weight of polyamide resin, (b) 1-45 parts by weight of an impact resistant component selected from the group consisting of ethylene propylene copolymer rubber (EPM), ethylene propylene rubber (EPR), ethylene propylene diene monomer rubber (EPDM), maleic anhydride modified ethylene propylene rubber (EPR-g-MA), maleic anhydride modified ethylene propylene copolymer rubber (EPM-g-MA), maleic anhydride modified ethylene propylenediene monomer rubber (EPDM-g-MA), arylmethacrylate-butadiene-styrene (MBS), styrene-butadiene-styrene triblock copolymer, all-acrylic core-shell rubber, ethylene ethylacrylate (EEA), styrene butadiene rubber (SBR), ethylene vinylalcohol (EVOH), various thermoplastic

elastomers and plastomers, or mixtures thereof, (c) 0.1-20 parts by weight of nylon plasticizer, (d) 0.01-5 parts by weight of nylon thickener having at least two functional groups at the ends of its polymer, and (e) 0.5-10 parts by weight of core-shell rubber.

5 Further, the present invention provides a polyamide resin composition characterized in that the polyamide is selected from the group consisting of nylon 6, nylon 7, nylon 8, nylon 10, nylon 2, nylon 66, nylon 69, nylon 610, nylon 611, nylon 612, nylon 6T, nylon 6/66, nylon 6/12, nylon 6/6T, or combinations thereof.

10 Further, the present invention provides a polyamide resin composition characterized in that the polyamide is a homopolymer; a copolymer blended or copolymerized with at least one selected from the group consisting of polyimide, polysulfone, polyethersulfone, polyphenylene sulfide, polyphenylene ether or polyphenylene oxide, high-impact polystyrene, acrylonitrile-butadiene-styrene
15 copolymer, acrylonitrile-ethylenepropylene-styrene, acrylonitrile-styrene-alkylacrylate, polycarbonate, polyethylene terephthalate and polybutyleneterephthalate; or a mixture of the homopolymer and the copolymer.

Further, the present invention provides a polyamide resin composition characterized in that the polyamide comprises semi-crystalline, amorphous
20 structures, or mixtures thereof.

Further, the present invention provides a polyamide resin composition characterized in that the nylon plasticizer is selected from the group consisting of lactams, sulfonamides, phthalates, adipates, phosphates, glycolates, or mixtures thereof.

25 Further, the present invention provides a polyamide resin composition characterized in that the nylon thickener is selected from the group consisting of

maleic anhydride modified polyolefin, maleic anhydride modified styrene resin and polyfunctional epoxy resin.

Further, the present invention provides a polyamide resin composition characterized in that the core-shell rubber comprises a hard polymer having a glass transition temperature of 25 °C or higher and a soft polymer having a glass transition temperature of 0 °C or higher.

Further, the present invention provides a polyamide resin composition characterized in that the hard polymer and the soft polymer in the core-shell rubber have a weight ratio of 1:9 to 9:1.

Further, the present invention provides a polyamide resin composition characterized in that the core-shell rubber contains 0.1-25 parts by weight of a reaction monomer on the basis of the whole weights of the core-shell rubber, the reaction monomer being selected from maleic acid, maleic anhydride, monoester or diester of maleic acid, tert-butylacrylate, acrylic acid, glycidylacrylate and vinyloxazoline, or mixtures thereof.

Further, the present invention provides a polyamide resin composition characterized by further comprising at least one selected from the group consisting of stabilizers, light stabilizers, heat stabilizers, UV stabilizers, lubricants, release agents, pigments, dyes, flame retardants, fiber reinforcing fillers, nucleating agents, or mixtures thereof.

In addition, the present invention provides a synthetic resin product prepared from the polyamide resin composition.

Further, the present invention provides a fuel tube for motor vehicles and a hose prepared from the polyamide resin composition.

Hereinafter, the invention will be defined in greater detail.

In the polyamide resin composition of the present invention, polyamide resin (A) can be obtained by homopolymerization or polycondensation of cyclic lactam having three rings or more, or α -amino acid, and may also be a product of condensation of a diacid and a diamine. In addition, homopolyamides, copolyamides or mixtures of the above polyamides may be used, in which the polyamide comprises semi-crystalline and/or amorphous structures.

As the homopolymerizable monomer, use can be made of ϵ -caprolactam, aminocaproic acid, oenantholactam, 7-aminoheptanoic acid, 11-aminoundecanoic acid, 9-aminononanoic acid, ϵ -piperidone, or mixtures thereof. In addition, a diamine can be polycondensed with a dicarboxylic acid to obtain polyamide polymer or copolymer, in which the diamine is selected from the group consisting of tetramethylene diamine, hexamethylene diamine, nonamethylene diamine, decamethylene diamine, undecamethylene diamine, dodecamethylene diamine, para-aminoaniline or meta-xylene diamine, and the dicarboxylic acid is exemplified by adipic acid, sebacic acid, dodecandioic acid, glutaric acid, terephthalic acid, 2-methyl terephthalic acid, isophthalic acid and naphthalene dicarboxylic acid.

In addition to diacids or diamines, polyfunctional compounds, such as trimellitic acid and pyromellitic acid, which have 3 or more functional groups, may be used in the range of 5 mol% or less. Parts of nylon monomer-remaining polyamide on polymerization may be also employed so as for increasing flexibility and viscosity. As the polyamide resin, nylons 6, 7, 8, 10, 2, 66, 69, 610, 611, 612, 6T, 6/66, 6/12 and 6/6T are used. Of them, nylon 6, nylon 66, and nylon 6/66 are preferably utilized. Further, blends having various content ratios and any combinations of these nylon resins may be used.

The polymerization method is any one selected from the group consisting of anionic polymerization, bulk melt polymerization, solution polymerization, melt polymerization through salt, interfacial polymerization, and reaction extrusion.

The polyamide copolymer obtained by polycondensing at least two monomers can be used, regardless of its component ratios.

With the intention of increasing weight, strength, heat resistance or impact resistance, the polyamide can be blended or copolymerized with any one of the group comprising polyimide, polysulfone, polyether sulfone, polyphenylene sulfide, polyphenylene ether or polyphenylene oxide (PPO), high-impact polystyrene (HIPS), acrylonitrile-butadiene-styrene (ABS) copolymer, acrylonitrile-ethylenepropylene-styrene (AES) copolymer, acrylonitrile-styrene-allylacrylate (ASA), polycarbonate (PC), polyethylene terephthalate (PET), or polybutylene terephthalate (PBT). Further, commercially available additives such as oxazoline modified polystyrene and maleic anhydride modified polyolefin may be used for improvement in performance of the above blends.

The component (A) is used in the amount of 30-95 parts by weight, and preferably, in the amount of 45-70 parts by weight.

The impact resistant component (B) is exemplified by EPM or EPR as two-member copolymer of ethylene propylene, EPDM as ethylene propylenediene monomer, allylmethacrylate-butadiene-styrene (MBS), styrene-butadiene-styrene (SBS) triblock copolymer, maleic anhydride modified EPM (EPM-g-MA), maleic anhydride modified SBS (SBS-g-MA), maleic anhydride modified EPDM (EPDM-g-MA), all-acrylic core-shell rubber, ethylene ethylacrylate (EEA), styrene butadiene rubber (SBR), ethylene vinylalcohol (EVOH), various thermoplastic elastomers and plastomers. Of them, it is preferred that EPM, EPDM, EPR, maleic anhydride modified EPM, maleic anhydride modified EPDM, and maleic anhydride modified EPR are used as the impact resistant component. Also, carboxylic acid or maleic anhydride may be added for improving the performance.

The above component (B) is used in the amount of 1-45 parts by weight, and preferably in the amount of 15-35 parts by weight, based on the total resin

composition.

The nylon plasticizer as the component (C) is responsible for increasing the flexibility of the composition, and includes, but is not limited to, lactams such as caprolactam and lauryl lactam; and sulfonamides, such as o,p-toluene sulfonamide and n-ethyl o,p-toluene sulfonamide.

Other plasticizers can be used, such as not only sulfonamides, trimellitates and polymer type plasticizers, but also phthalates, adipates, phosphates, and glycolates.

Further, the other available plasticizers is disclosed in U.S. Pat. No. 4,197,379. The component (C) is added in the amount of 0.1-20 parts by weight based on the total resin composition. Preferably, it is used in the amount of 5-15 parts by weight.

However, as the component (C) is increased in its amounts, the resin composition has improved flexibility but has an unsuitable melt index for extrusion or blow molding. Thus, the component (D) having at least two functional groups at the ends of its polymer chain is used, such that the resin composition has an appropriate melt index. Representative of the component (D) is styrene maleic anhydride resin (SMA) of maleic anhydride modified polymer structure, and modified polyolefins, or polymers having similar reactive groups. In addition, polyfunctional epoxy resins, such as cresol novolac epoxy and phenol novolac epoxy, may be used.

The component (D) is used in the amount of 0.01-5 parts by weight, and preferably in the amount of 0.1-3 parts by weight, of the total resin composition.

The component (E) of the present invention, for further improving the external appearance of molded products, elongation under tension, impact resistance under cold environment, is a core shell type rubber comprising at least

one hard portion and soft portion. The hard portion and the soft portion comprise a polymer having glass transition temperature of 25 °C or higher and a polymer having glass transition temperature not more than 0 °C, respectively. Such composition has a single core and at least one shell structure, in which the structure is determined by the added monomer sequences. Examples of the soft portion include butadiene, isoprene, alkylacrylate, alkylmethacrylate or siloxane, and comonomer-derived materials. Preferred core-shell rubber includes one soft core and a single hard shell. The reactive groups comprise carbonyl, carboxyl, anhydride, amido, imido, carboxylic ester, amino, hydroxyl, epoxy, oxazoline, urethane, urea, lactam or halobenzene group. The polymerization of the final shell is carried out by addition of a monomer having suitable reactive groups. For example, suitable reaction monomers comprise maleic acid, maleic anhydride, monoesters or diesters of maleic acid, tert-butylacrylate, acrylic acid, glycidylacrylate, and vinyloxazoline.

Such reaction monomer is used in the amount of 0.1-25 parts by weight and preferably in the amount of 0.25-15 parts by weight, to the whole weights of the core-shell rubber. The ratio of the soft component and the hard component is 1:9 to 9:1, and preferably 3:7 to 8:2. EP-A-208187 discloses such rubber. The component (E) is added in the amount of 0.1-10 parts by weight, and preferably, in the amount of 0.5-5 parts by weight, on the basis of the total resin composition.

To the composition of the present invention, essential additives, such as stabilizers, stabilizing agents resistant to light, heat and UV, lubricants, release agents, pigments, dyes, flame retardants, fiber reinforcing fillers, and nucleating agents may be added, within the scope of not affecting physical properties, external appearance and workability of final articles.

Representative antioxidants and heat stabilizing agents are metal halogenides, namely, sodium, potassium, lithium, copper halogenides, and

chlorine, bromine, zinc, hindered phenol, various phosphates, hydroquinones, or mixtures thereof.

As the UV stabilizing agent, use can be made of resorcinols, salicylates, hindered amines, benzotriazoles and benzophenols. As for the lubricants and the release agents, stearic acid, stearyl alcohol, stearamides, wax, carbonate ester, and carbonate metallate are used. Nigrosine is used as organic dyes, and as pigments, use is made of titanium dioxide, cadmium sulfide, selenite cadmium, ultramarine blue, carbon black.

As the flame retardants, organic halogen compound and non-halogen compounds, and metal hydroxide compounds are used.

Further, as for common reinforcing fillers, glass fibers, glass beads, glass flakes, mica, talc, carbon fibers, kaolin, wallastonite, molybdenum disulfide, potassium titanate, barium sulfate, conductive carbon black, and aramid fibers are representatively used. In addition, fire-proofing agents, anti-drip agents, magnetic agents, EMI masking agents, antibacterial agents, antimicrobial agents, metal deactivators, far infrared radiation agents, and antistatic agents may be included.

The resin composition components of the present invention, along with essential additives (lubricants, stabilizers etc.), are primarily mixed by use of a super mixer, and then blended by a twin-screw extruder, a single-screw extruder, roll-mill, kneader or banbury mixer, and preferably by twin-screw extruder, under no vacuum, to obtain a pellet using a pelletizer, which is then sufficiently dried in a dehumidifier, injected and measured for its physical properties.

A better understanding of the present invention may be obtained in light of the following examples which are set forth to illustrate, but are not to be construed to limit the present invention.

EXAMPLES 1-11

Nylon 6, caprolactam, maleic anhydride modified EPM rubber (EPM-g-MA), sulfonamide plasticizer (liquid), core-shell rubber, thickener, and carbon black masterbatch were mixed according to the ratios of the following table 1, blended using a twin-screw extruder at 240 °C, pelletized with a pelletizer and then dried at 70 °C and 90 °C over time in a dehumidifier. While changing rotation rates of the screw, the composition was dried at 70 °C in a dehumidifier for a predetermined period of time, and molded in an injector. The injected pieces were measured for physical properties and external appearance according to the following standard method. With the intention of examining the dispersability of the rubber, a thin film was made and observed with an optical microscope.

Physical Properties Test Method

Tensile strength and elongation : ASTM D 638, 50 mm/min.

Flexible strength and flexible elastic modulus : ASTM D 790, 10 mm/min.

Izod impact strength, room temperature and 40 °C : ASTM D 256, 1/4 inch thick test piece, izod notched.

Melt Index : ASTM D 1238 235 °C, 2.16 kgf.

* Gasoline resistance test

Gasoline 50 °C, after 48 and 96 hours

Flexible strength and flexible elastic modulus : ASTM D 790 10 mm/min.

External appearance assay

The compositions obtained at different screw rotation rates were made to

0.05 mm thick films, and the dispersed rubber state in the films was observed by an optical microscope. External appearance was assayed by naked eye.

Good dispersability, smooth surface observed by naked eye : ●

Very small rubber lumps, fine projections on molded product observed by
5 naked eye : ▲

Large rubber lumps, many projections on molded product observed by
naked eye : ×

COMPARATIVE EXAMPLE 1

Expensive nylon elastomer reinforced polyamide 6 resin composition was
10 dried at 150 °C for 12 hours and sintered at 950 °C for 12 hours.

The polyamide resin composition was blended in a twin-screw extruder at 250 rpm, pelletized by use of a pelletizer and then dried at 70 °C for 5 hours in a dehumidifier, thus measuring its general physical properties. The results are shown in Table 1, below, in which each component has the unit of parts by weight.

15 TABLE 1

	Ex. No.											C.Ex.
	1	2	3	4	5	6	7	8	9	10	11	1
Nylon 6	59.8	59.3	55.8	53.3	54.3	51.8	54.8	52.8	58.2	55.5	57.8	55.0
Caprolactam	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0
EPDM-g-MA	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	.
Nylon Elastomer	35.0
Sulfonamide Based material	.	0.5	1.5	1.5	3.0	3.0	5.0	7.0	1.5	1.5	1.5	.

Thickener	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.3	0.5	0.7	-
Core-shell rubber	-	-	2.5	5.0	2.5	5.0	-	-	-	2.5	-	-
Carbonblack masterbatch	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
Melt Index (-g/10min)	0.5	0.7	1.0	0.8	1.5	1.1	3.2	4.3	1.3	0.08	0.6	1.1
Tensile strength (kg/cm ²)	405	405	405	400	390	385	400	350	420	405	420	400
Elongation (%)	235	245	280	290	285	300	265	270	220	255	205	210
Flexible Strength (kg/cm ²)	244	240	230	210	210	200	235	185	250	218	260	210
Flexible elastic modulus (kg/cm ²)	6200	6000	5600	5100	5000	4600	4100	3600	5200	5000	6500	4750
Impact strength (23°C, kg-cm/cm)	NB	NB	NB	NB	NB	NB	NB	NB	NB	NB	NB	NB
Impact strength (-40°C, kg-cm/cm)	17.0	18.8	20.2	21.6	19.0	22.3	17.3	17.9	16.1	19.6	16.5	10.5
External Appearance	×	▲	●	●	●	●	▲	▲	×	●	×	▲
Plasticizer Dissolution	●	●	●	●	▲	▲	×	×	●	●	●	●

The properties of the resin composition of the example 4 in the above table 1, which were equal to or better than those of nylon elastomer reinforced polyamide 6 resin composition, were measured according to temperature and time in a

dehumidifier, and dissolution of the plasticizer was tested (screw rotation rate : 250 rpm). The results are given in the following table 2.

TABLE 2

	Ex.No. 4, Dehumidifier 70°C			C.Ex., Dehumidifier 70°C		
	3h	5h	9h	3h	5h	9h
Melt Index (-g/10min)	0.9	0.8	0.8	1.3	1.1	1.1
Tensile Strength (kg/cm ²)	390	400	385	380	400	390
Elongation (%)	245	290	230	185	210	190
Flexible Strength (kg/cm ²)	195	210	222	198	210	225
Flexible Elastic modulus (kg/cm ²)	4900	5100	5210	4600	4750	5150
Impact Strength (23°C, kg-cm/cm)	NB	NB	NB	NB	NB	NB
Impact Strength (-40°C, kg-cm/cm)	21.1	21.6	21.3	10.0	10.5	9.3
Plasticizer dissolution	●	●	▲	●	●	▲

- 5 The properties of the resin composition of the example 4 in the above table 1, which were equal to or better than those of nylon elastomer reinforced polyamide 6 resin composition, were measured according to temperature and time in a dehumidifier, and dissolution of the plasticizer was tested. The results are given in

Table 3, below.

TABLE 3

	Ex. No. 4 Dehumidifier 90°C			C.Ex. 1 Dehumidifier 90°C		
	3h	5h	9h	3h	5h	9h
Melt Index (-g/10min)	0.8	0.8	0.7	1.0	1.0	0.9
Tensile Strength (kg/cm ²)	410	400	380	395	387	370
Elongation (%)	270	255	225	210	185	165
Flexible Strength (kg/cm ²)	218	238	255	210	235	251
Flexible Elastic modulus (kg/cm ²)	5150	5300	5700	4900	5250	5900
Impact Strength (23°C, kg-cm/cm)	NB	NB	NB	NB	NB	NB
Impact Strength (-40°C, kg-cm/cm)	21.2	20.0	18.4	10.7	10.1	9.3
Plasticizer dissolution	▲	×	×	×	×	×

The resin composition of the example 4 in the above table 1, having properties equal to or better than those of nylon elastomer reinforced polyamide 6, was measured for properties varying with screw rotation rates, and the external appearance of 0.05 mm thick film was observed by an optical microscope (dehumidifier 70 °C, 5 hours). The results are given in Table 4, below.

TABLE 4

	Ex.No. 4, screw rotation rate			C.Ex.
	150	250	350	1
Melt Index (-g/10min)	1.2	0.8	0.8	1.1

Tensile Strength (kg/cm ²)	370	400	410	390
Elongation (%)	210	290	305	210
Flexible Strength (kg/cm ²)	205	210	210	210
Flexible Elastic modulus (kg/cm ²)	5000	5100	5150	4750
Impact Strength (23°C, kg-cm/cm)	NB	NB	NB	NB
Impact Strength (-40°C, kg-cm/cm)	18.5	21.6	21.8	10.5
Microscope Observation	×	▲	●	▲

As can be seen in the above table 4, physical properties and external appearance of the composition prepared at screw rotation of 350 rpm after drying at 70 °C for 5 hours in a dehumidifier are equal to or better than those of nylon elastomer reinforced polyamide 6.

The resin compositions of the example 4 and the comparative example 1 were immersed in gasoline at 50 °C for 48 hours and 96 hours, after which their properties and whiteness were measured. The results are presented in the following table 5.

10 TABLE 5

	Ex. No. 4			C. Ex.		
	After Injection	After 48h	After 96h	After Injection	After 48h	After 96h
Oil Absorption(%)	—	0.14	0.17	—	0.12	0.15
Flexible Strength(kg/cm ²)	210	250	255	210	246	250

Flexible Elastic Modulus(kg/cm ²)	5100	5700	5750	4750	5550	5600
External Appearance	●	●	●	▲	▲	▲
Whiteness	No	No	No	No	No	No

5 The polyamide composition of the present invention comprising 30-95 parts by weight of polyamide resin, 1-45 parts by weight of an impact resistant component, 0.1-20 parts by weight of nylon plasticizer, 0.01-5 parts by weight of nylon thickener having at least two functional groups at the ends of its polymer chain and 0.5-10 parts by weight of core-shell rubber, is higher in flexibility, moldability and external appearance, and also much lower in price, compared to a conventional nylon elastomer reinforced polyamide resin composition. Thus, the composition is effectively applicable to internal and external decorative components for motor vehicles, and electrical or electronic components.

10 The present invention has been described in an illustrative manner, and it is to be understood that the terminology used is intended to be in the nature of description rather than of limitation. Many modifications and variations of the present invention are possible in light of the above teachings. Therefore, it is to be understood that within the scope of the appended claims, the invention may
 15 be practiced otherwise than as specifically described.